

AS1525 1 part Industrial Adhesive Sealant

Description

This is a 1-part, RTV (Room Temperature Vulcanizing) silicone adhesive sealant. It is one in a range of Acetoxy cure products which are solvent free. During cure, it liberates a very small amount of acetic acid, giving rise to the familiar 'vinegar' odor, which quickly dissipates after cure. It exhibits good primer-less adhesion to many substrates including but not limited to; aluminum, non ferrous metals, steel, glass, enameled surfaces, fabrics ceramics, thermosetting, thermoplastics and wood and cures rapidly at room temperature when in contact with atmospheric moisture. This product is not to be recommended for use with galvanized metals, ferrous metals, copper and its associated alloys or in electronic assemblies.

Key Features

- Fast room temperature cure
- Controlled through to prevent strike through on textiles
- Excellent elongation

Application

Applications include but not limited to, textiles, stocking grippers, medical stocking grippers

These products are highly resistant to weathering and aging, largely stable to many solvents, oils, water, sea water, industrial waste gasses, diluted acids, saline solutions detergents, cleaners, propellants and fruit acids.

Use and Cure Information

This product is a ready for use 1 Part system and can be directly dispensed from the original container without mixing. If supplied in cartridges it can be applied using either manual or pneumatic dispensing guns. It can also be applied from bulk containers using conventional drum dispensing equipment.

All surfaces to which the sealant is to be applied should be clean, dry and free from grease, dust, dirt, and loose material. Priming of surfaces is not normally required but in some cases it may be necessary to pretreat the surface. Please check this in each individual case. For degreasing of non-porous surfaces such as metal, and glass, KORASOLV GL is recommended (use undyed crepe paper or similar). If using as an adhesive, it should be applied to one clean surface and the other clean surface brought into contact with it within the stated tack free time. For optimum bond strength, the thickness of the sealant joint should be a minimum of 1 mm.

The sealant will cure upon exposure to atmospheric moisture, ideally between 20 to 70 °C and >40% humidity. Time taken for cure will depend on the thickness of the joint, humidity and temperature. Increasing the temperature and humidity will accelerate the curing process, do not cure the sealant at or above 70°C as bubbles may form in the sealant and affect the overall physical properties and adhesion. Low temperatures and humidity will retard the curing process. Since curing times progressively increase with the thickness, the sealant depth should be limited to 10 mm. Joints should be left undisturbed for at least 24 hours, but preferably longer to effect sufficient depth of cure. Full cure requires 7 days at thicknesses of 1 - 5 mm and 14 days at thicknesses of 5 - 10 mm.

"For pneumatic dispensing of 310 ml cartridges, the recommended pressure is 2.25 to 3.45 bar (40 to 50 psi). Dispensing pressure above the recommended limits may lead to gas bypassing the piston, causing spluttering at the nozzle and poor bead quality"

Solvents and cleaning agents.

For cleaning of the substrates to be bonded : KORASOLV GL.

For cleaning working tools and for removing fresh uncured material: KORASOLV GL

Care must be taken when cleaning synthetic materials which tend to form stress cracks, for example, polycarbonate and acrylic. Please contact our technical service team for advice.

For removal of vulcanized product this can be done by mechanical means or by use of a chemical digester, please contact our technical service team for advice.

Health & Safety

Health and Safety

Property

Uncured Product

| Property | Test Method | Value |
|--|-------------|-------------------------------|
| Appearance | | Viscous liquid |
| Cure Profile | | 23+/-2°C and 50+/-5% humidity |
| Cure Through to 3 mm Depth | | 24 hr |
| Cure Type | | Acetoxy |
| Rheology | | Flowable |
| Self Bonding | | Yes |
| Tack Free Time / Skin Formation at 23°C/73°F | | 7 min |
| Viscosity Mixed | Brookfield | 60000 cP |

Cured Product

7 days at 23+/-2°C and 50+/-5% humidity

| | | |
|--|----------------|---------------------|
| 100% Modulus (N/mm2) | | 0.5 MPa / 73 psi |
| CTE Linear ppm/°C | | 297 ppm / °C |
| CTE Volumetric ppm/°C | | 892 ppm/°C |
| Color | | Translucent |
| Density | BS ISO 2781 | 1.01 g/cm3 |
| Elongation at Break | ISO 37 | 190 % |
| Hardness Shore A | ASTM D 2240-95 | 30 |
| Linear Coefficient of Thermal Expansion (ppm/°C) | | 297 ppm/°C |
| Max Working Temp | | 250 °C / 482 °F |
| Min Working Temp | | -50 °C / -58 °F |
| Tensile Strength | ISO 37 | 1 N/mm2 / 145 psi |
| Thermal Conductivity | | 0.2 W/mK |
| Youngs Modulus (N/mm2) | | 0.35 N/mm2 / 51 psi |

Electrical Properties

| | | |
|------------------------------|------------|-----------------|
| Dielectric Constant | ASTM D-150 | 3 |
| Dissipation Factor | ASTM D-150 | 0.0025 |
| Volume Resistivity (Ohms cm) | ASTM D-257 | 1.4E+14 ohms cm |

Storage

| | |
|-------------------------|----------------|
| Max Storage Temperature | 40 °C / 104 °F |
| Shelf Life | 12 mths |

The content set out in the technical data sheet does not contain information upon which you should rely. It is provided for general information purposes only and does not constitute a product specification. You must obtain professional or specialist advice before taking any action based on the information provided in the technical data sheet.

CHT make reasonable efforts to ensure that information set out in the technical data sheet is complete, accurate, and up-to-date. CHT do not, however, make any representations, warranties or guarantees (whether express or implied) that information set out in the technical data sheet is complete, accurate, or up-to-date or that the product will be suitable for your requirements. You should carry out your own testing to determine the applicability of such information and whether the product will be suitable. CHT reserve the right to modify the technical data sheet at any time. The CHT technical service department is available to offer further information and advice and should it be needed to look at modifying current products or custom formulate a new one to meet your specific requirements. Please contact the technical service department.

CHT Germany GmbH: Postfach 12 80, 72002 Tübingen, Bismarckstraße 102, 72072 Tübingen, Germany

Telephone: 07071/154-0, Fax: 07071/154-290, Email: info@cht.com, Homepage: www.cht.com / www.cht-silicones.com

Safety Data Sheets available on request.

Packaging

CHT Adhesives are available in a variety packaging including cartridges and bulk containers. Please contact our sales department for more information.

Revision Date 29 Apr 2021
Revision No 1
Download Date 27 Apr 2024