

EM 1469 55% Active Emulsion of a 60,000 cSt Polydimethylsiloxane

Description

This product is an industrial nonionic polydimethylsiloxane emulsion.

Key Features

- Excellent wetting and spreading
- High molecular weight for extended performance
- APE Free
- Easily dispersed in water with minimal agitation

Key Applications

- Release agent
- Rubber treatment
- Casting
- Extrusion

Application

EM 1469 is a 55% active emulsion of a high molecular weight silicone polymer. The high molecular weight dimethicone actives are delivered in an opaque, low viscosity liquid with neutral pH.

This emulsion was developed as an effective release agent at low concentrations. EM 1469 is used in a variety of release applications as well as a leather conditioner, vinyl dressing and rubber treatment

Use and Cure Information

To optimize the dispersion of this emulsion into the final formulation, it is recommended to add it slowly at the end of the procedure at a temperature below 40 °C (104 °F) with continuous mixing or stirring.

Health & Safety

Read product and safety data sheets before handling this product for physical and health hazard information. The safety data sheet is available from your CHT representative.

Limitations

This product is not intended for pharmaceutical use.

Property

Test Method Value

Product

Appearance	White Liquid
Ionicity	Non-ionic
Solids Content (%)	55 %
pH	7.5

Addition Rates

Dosage - 1	0.1 - 1%
------------	----------

Storage

Max Storage Temperature	40 °C / 104 °F
Packaging	40 lb. pails, 441 lb. drums, 2205 lb. totes, and tanker
Shelf Life	12 mths

Revision Date 12 Feb 2024

Revision No 7

Download Date 28 Apr 2024

The content set out in the technical data sheet does not contain information upon which you should rely. It is provided for general information purposes only and does not constitute a product specification. You must obtain professional or specialist advice before taking any action based on the information provided in the technical data sheet. CHT make reasonable efforts to ensure that information set out in the technical data sheet is complete, accurate, and up-to-date. CHT do not, however, make any representations, warranties or guarantees (whether express or implied) that information set out in the technical data sheet is complete, accurate, or up-to-date or that the product will be suitable for your requirements. You should carry out your own testing to determine the applicability of such information and whether the product will be suitable. CHT reserve the right to modify the technical data sheet at any time. The CHT technical service department is available to offer further information and advice and should it be needed to look at modifying current products or custom formulate a new one to meet your specific requirements. Please contact the technical service department.

CHT Germany GmbH: Postfach 12 80, 72002 Tübingen, Bismarckstraße 102, 72072 Tübingen, Germany
Telephone: 07071/154-0, Fax: 07071/154-290, Email: info@cht.com, Homepage: www.cht.com / www.cht-silicones.com