

TECHNICAL DATA SHEET

QLE 1050 Addition Cure, One Part Coating

Description

This is a 100% silicone solids, one part elastomer designed for use as a conformal coating, but can also be used for cloth coating applications.

Key Features

- 100% solids
- Transparent, ideal for pigmentation
- Fast cure at elevated temperatures

Application

Conformal coating for PCB's and cloth coating

CURE PROFILE	
TEMPERATURE	TIME
200 °C	15 seconds
150 °C	< 60 seconds

Use and Cure Information

This material is a one-component, translucent, heat-cured silicone elastomer. The material should only be used on clean surfaces to maximize adhesion properties. In addition, some substrates may be difficult to bond to and some, such as galvanized metal, may cause cure inhibition. A primer can be used to eliminate this problem.

Revision Date 12 Oct 2021
Revision No 4
Download Date 09 May 2024

Property

Uncured Product

Color	Clear to light brown
Cure Type	Addition
Rheology	Liquid
Specific Gravity	0.97
Viscosity	500 cP

Test Method

Value

Cured Product

10 minutes at 150°C

Hardness Shore A	ASTM D 2240-95 30
Max Working Temp	204 °C / 399 °F
Min Working Temp	-55 °C / -67 °F
Refractive Index	1.40
Thermal Conductivity	0.14 W/mK

Storage

Max Storage Temperature	4.4 °C / 40 °F
Shelf Life	12 mths

The content set out in the technical data sheet does not contain information upon which you should rely. It is provided for general information purposes only and does not constitute a product specification. You must obtain professional or specialist advice before taking any action based on the information provided in the technical data sheet. CHT make reasonable efforts to ensure that information set out in the technical data sheet is complete, accurate, and up-to-date. CHT do not, however, make any representations, warranties or guarantees (whether express or implied) that information set out in the technical data sheet is complete, accurate, or up-to-date or that the product will be suitable for your requirements. You should carry out your own testing to determine the applicability of such information and whether the product will be suitable. CHT reserve the right to modify the technical data sheet at any time. The CHT technical service department is available to offer further information and advice and should it be needed to look at modifying current products or custom formulate a new one to meet your specific requirements. Please contact the technical service department.

CHT Germany GmbH: Postfach 12 80, 72002 Tübingen, Bismarckstraße 102, 72072 Tübingen, Germany
Telephone: 07071/154-0, Fax: 07071/154-290, Email: info@cht.com, Homepage: www.cht.com / www.cht-silicones.com