

QSiil 40 2 part encapsulation and potting silicone

Description

QSiil 40 is a general purpose two-part, room temperature, condensation cure siloxane elastomer. The two applicable catalysts are 0.5% DBT by weight and 10% Deep Section Catalyst by weight. Cure speed can be accelerated by adding DBT catalyst in increments of 0.1%. This will not alter the physical properties of the material. QSiil 40 exhibits excellent release properties. However, strong adhesion can be achieved through the use of a primer.

Key Features

- Good adhesion with use of a primer
- Self-levelling
- Variable cure speed
- UL recognized in file No. E205830

Use and Cure Information

MIXING

If using QSiil Deep Section Catalyst as the curing agent, it should be thoroughly mixed prior to use. QSiil 40 should be catalyzed by weight with the appropriate amount of curing agent. A concentration of 0.5% DBT catalyst or 10% Deep Section Catalyst will provide a cure time of 24 hours. Cure speed can be accelerated by adding DBT catalyst in increments of 0.1%. Material should be mixed in a clean, compatible metal or plastic container. The volume of the container should be 4 – 5 times the volume of the material to be catalyzed. Thoroughly mix using clean tools, scraping the bottom and the side of the container to produce a homogeneous mixture.

DE-AERATION

Air trapped during mixing should be removed to eliminate voids in the cured product. Vacuum de-airing may be necessary to completely remove all entrapped air bubbles. To ensure proper de-airing, subject the mixed material to 29 inches of mercury.

When using QSiil 40 for potting, a de-aeration step may be necessary after pouring to avoid capturing air in complex assemblies.

DEEP SECTION CURE

Cured QSiil 40 should be properly conditioned prior to service if it is to be used in deep sections at temperatures over 150 °C (32 °F). Following room temperature cure of 1 – 3 days, a typical program would be eight hours at 50°C intervals from 100 °C (212 °F) to the service temperature. Longer times at each temperature will be required for larger parts of very deep sections.

BONDING

QSiil 40 rubber compounds require a primer to bond to non-silicone surfaces. Thoroughly clean the substrate with a non-oily solvent such as naphtha or methyl ethyl ketone (MEK) and let the surface dry. Then apply a uniform thin film of a suitable silicone primer to air dry for one hour or more.

Property

Uncured Product

Cure Profile		24 hrs at room temperature
Cure Type		Condensation
Density A	BS ISO 2781	1.2
Density B	BS ISO 2781	1.04
Gel Time at 25°C/77°F		100 min
Rheology		Liquid
Tack Free Time / Skin Formation at 23°C/73°F		4 hr
Viscosity A	Brookfield	11000 cP
Viscosity Mixed	Brookfield	11000 cP

Cured Product

Color		White
Elongation at Break	ISO 37	200 %
Hardness Shore A	ASTM D 2240-95	40
Max Working Temp		204 °C / 399 °F
Min Working Temp		-55 °C / -67 °F
Tear Resistance (N/mm)	BS ISO 34-1	3.47 N/mm / 20 ppi
Tensile Strength	ISO 37	1.38 N/mm² / 200 psi
UL File No.		E205830

Storage

Max Storage Temperature	4.4 °C / 40 °F
Shelf Life	12 mths

UNCATALYZED			
TEST	QSil 40	DBT Catalyst	Deep Section Catalyst
Appearance	White	Clear/light yellow	Beige
Viscosity	11,000 cps	N/A	6,500 cps
Specific Gravity	1.20	1.04	1.47

CATALYZED		
	DBT Catalyst MIX RATIO 100:0.5 by weight	Deep Section Catalyst MIX RATIO 10:1 by weight
PROPERTY	RESULT	RESULT
Gel Time at 25 °C *	100 minutes	45 minutes
Tack Free Time	4 hours	2 hours

* Gel time is defined as the time required for the material to become a solid or a semi-solid.

24 HOUR Room Temperature Cure with Deep Section Catalyst	
PROPERTY	RESULT
Durometer, Shore A	40
Tensile	200 psi
Elongation	200%
Tear B	20 ppi
Useful Temperature Range	-55 °C – 204 °C

Storage

See product label and/or CoA for specific "Use By Date". Product should be stored in its original, unopened container. Storage beyond the date specified on the label does not necessarily mean that the product is no longer usable. In this case, the properties required for the intended use should be checked for quality assurance reasons

Revision Date 29 Apr 2021
Revision No 1
Download Date 30 Apr 2024

The content set out in the technical data sheet does not contain information upon which you should rely. It is provided for general information purposes only and does not constitute a product specification. You must obtain professional or specialist advice before taking any action based on the information provided in the technical data sheet. CHT make reasonable efforts to ensure that information set out in the technical data sheet is complete, accurate, and up-to-date. CHT do not, however, make any representations, warranties or guarantees (whether express or implied) that information set out in the technical data sheet is complete, accurate, or up-to-date or that the product will be suitable for your requirements. You should carry out your own testing to determine the applicability of such information and whether the product will be suitable. CHT reserve the right to modify the technical data sheet at any time. The CHT technical service department is available to offer further information and advice and should it be needed to look at modifying current products or custom formulate a new one to meet your specific requirements. Please contact the technical service department.

CHT Germany GmbH: Postfach 12 80, 72002 Tübingen, Bismarckstraße 102, 72072 Tübingen, Germany
Telephone: 07071/154-0, Fax: 07071/154-290, Email: info@cht.com, Homepage: www.cht.com / www.cht-silicones.com