

QSiil 550 2 part encapsulation and potting silicone

Description

QSiil 500 series are 100% silicone solids elastomer designed for electronic potting and encapsulation applications. The two-component system offers a flame retardant, thermally conductive, low modulus material that is readily repairable.

Key Features

- Long pot life
- Low modulus and good elongation
- 275 °C Max Working Temp, test method AFS1540B
- UL94 V0 listed in file No. E205830

Application

QSiil 550 is designed for potting electronics to provide environmental protection (e.g. Sterilization units). Suitable for higher working temperatures.

Use and Cure Information

Mixing:

In order to achieve optimum performance, the same lot number of A and B should be used. The A and B parts should be thoroughly mixed prior to catalyzation.

Mixing by hand: Catalyze the A part with the B part at the designated mix ratio by weight using a clean plastic or metal container of approximately 3 times the volume of the material and mix by hand. Accurate weighing of all components, on a suitable scale, is essential for optimal product performance when mixing by hand. Mix until the material is uniform with no visible striations.

Mixing and dispensing with automatic equipment: Use a mixing system that will properly mix the A and B parts at the designated ratio by weight.

De-aeration:

Air trapped during mixing should be removed by vacuum at 29 inches of mercury. During the process, the material will expand, and intermittent evacuation may be required. Machine mixed material does not normally need to be de-aired.

Health & Safety

Safety Data Sheets available on request.

Packaging

CHT Encapsulating and potting compounds are available in a variety packaging including bulk containers. Please contact our sales department for more information.

Storage:

This product is best when used within the "Use by Date". See product label and/or CoA for specific "Use by Date". Product should be stored in its original, unopened container. Storage beyond the date specified on the label does not necessarily mean that the product is no longer usable. In this case, the properties required for the intended use should be checked for quality assurance reasons.

Revision Date 12 Feb 2024
Revision No 6
Download Date 30 Apr 2024

Property

Uncured Product

Color A		Beige
Color B		Black
Cure Profile		7 mins at 150°C
Cure Type		Addition
Density A	BS ISO 2781	1.41
Density B	BS ISO 2781	1.41
Gel Time at 25°C/77°F		130 min
Mix Ratio By Weight		1:1
Rheology		Liquid
Self Bonding		No
Viscosity Mixed	Brookfield	4000 cP

Cured Product

7 minutes at 150°C		
Color		Gray
Elongation at Break	ISO 37	150 %
Hardness Shore A	ASTM D 2240-95	55
Max Working Temp		275 °C / 527 °F
Min Working Temp		-55 °C / -67 °F
Tear Resistance (N/mm)	BS ISO 34-1	5.73 N/mm / 33 ppi
Tensile Strength	ISO 37	3.52 N/mm ² / 510 psi
Thermal Conductivity		~0.37 W/mK
UL 94V-0		Yes
UL File No.		E205830

Electrical Properties

Dielectric Constant	ASTM D-150	3.12
Dielectric Strength kV/mm	ASTM D-149	20.3 kV/mm / 516 V/mil
Dissipation Factor	ASTM D-150	0.003
Volume Resistivity (Ohms cm)	ASTM D-257	1.47E+15 ohms cm

Storage

Max Storage Temperature	38 °C / 100 °F
Shelf Life	24 mths