

SE2011 2 part encapsulation and potting silicone

Description

This is a self-bonding 2-component, silicone elastomer system specially designed for electronic potting and encapsulation applications. It offers good protection against chemicals, environmental contamination, mechanical shock, vibration and impact damage. It can be employed in areas where low flammability is a prerequisite. The cured elastomer can be repaired. The component parts have relatively low viscosities and are readily mixed either by hand or machine.

This silicone elastomer has the benefit of developing chemical adhesion to a variety of substrates and is compatible with many sensitive substrates including copper, brass, steel, aluminium, FR4, and plastics making this an ideal option where fast curing and adhesion are needed without the use of a primer.

Key Features

- Adhesive at room temperature
- Fast curing at room temperature
- Low viscosity
- UL recognised in file No. E334038

Application

Junction box potting for solar / photovoltaic cells

Use and Cure Information

The product is supplied as two components 'A' and 'B'. These components should be mixed together in the ratio by weight shown opposite. Mixing can be done by hand or by automated dispensing machine using a static mixer nozzle. A nozzle of at least 9 GXF type elements is recommended for uniform mixing of both components.

The dispensing machine mix ratios should be adjusted if mixing by volume and not weight. IMPORTANT the mixed components will cure in the nozzle so to preserve nozzles a continuous process is required or a change of nozzle after the task is completed. Complete mixing of each component is achieved within the first 50-60% of the nozzle.

Mixing

Both the 'A' and 'B' parts should be well stirred to ensure the material is uniform and any settlement of the fillers have been remixed.

Place the required amount of 'A' and 'B' parts by weight at the mix ratio shown opposite, in a clean plastic or metal container of approximately 3 times their volume, and mix until the colour of the mixture is uniform. For best results, we recommend degassing. Degassing by intermittent evacuation, the larger volume of the mixing vessel helps prevent overflow during this operation. In case of automatic dispensing with static mixing head, the two components should be degassed before processing. Recommended vacuum conditions are 30-50 mbar intermittently over 5-10 minutes. Cast the mixture either by gravity or pressure injection.

Adhesion

Ensure all substrates are clean and free of surface contaminants. A Solvent degreaser is recommended for metallic substrates and Iso-propanol solvent is recommended for plastics and polycarbonates. A mechanical bond to the substrates will develop shortly after applying. A chemical bond will develop after 24 hours and maximum adhesion is reached after 7 days.

It is important to check the compatibility in preliminary tests if unknown substrates are used.

Health & Safety

Health and Safety

Safety Data Sheets available on request.

Packaging

CHT Encapsulants are available in a variety of packaging including bulk containers. Please contact our sales department for more information.

Property

Uncured Product

| Property | Test Method | Value |
|--|-------------|--------------|
| Cure Type | | Condensation |
| De-mould Time / Full Cure at 23°C/73°F | | 2 hrs |
| Density A | BS ISO 2781 | 1.05 |
| Density B | BS ISO 2781 | 0.83 |
| Mix Ratio By Weight | | 10:1 |
| Pot Life mins at 23°C/73°F | | 20 min mins |
| Rheology | | Liquid |
| Self Bonding | | Yes |
| Viscosity A | Brookfield | 4400 cP |
| Viscosity B | Brookfield | 100 cP |
| Viscosity Mixed | Brookfield | 4000 cP |

Cured Product

7 days at 23+/-2°C and 50+/-5% humidity

| | | |
|--|----------------|---------------------|
| CTE Volumetric ppm/°C | | 837 ppm/°C |
| Color | | Black |
| Density | BS ISO 2781 | 1.08 g/cm3 |
| Elongation at Break | ISO 37 | 270 % |
| Hardness Shore A | ASTM D 2240-95 | 23 |
| Linear Coefficient of Thermal Expansion (ppm/°C) | | 279 ppm/°C |
| Linear Shrinkage (%) | | 2.8 % |
| Max Working Temp | | 220 °C / 428 °F |
| Min Working Temp | | -50 °C / -58 °F |
| Tensile Strength | ISO 37 | 0.9 N/mm2 / 131 psi |
| Thermal Conductivity | | 0.2 W/mK |
| UL File No. | | E334038 |
| Youngs Modulus (N/mm2) | | 0.29 N/mm2 / 42 psi |

Electrical Properties

| | | |
|------------------------------|------------|------------------------|
| Dielectric Constant | ASTM D-150 | 3.28 |
| Dielectric Strength kV/mm | ASTM D-149 | 23.4 kV/mm / 594 V/mil |
| Dissipation Factor | ASTM D-150 | 0.029 |
| Volume Resistivity (Ohms cm) | ASTM D-257 | 1.09E+14 ohms cm |

Storage

| | |
|-------------------------|----------------|
| Max Storage Temperature | 40 °C / 104 °F |
| Shelf Life | 6 mths |

The content set out in the technical data sheet does not contain information upon which you should rely. It is provided for general information purposes only and does not constitute a product specification. You must obtain professional or specialist advice before taking any action based on the information provided in the technical data sheet.

CHT make reasonable efforts to ensure that information set out in the technical data sheet is complete, accurate, and up-to-date. CHT do not, however, make any representations, warranties or guarantees (whether express or implied) that information set out in the technical data sheet is complete, accurate, or up-to-date or that the product will be suitable for your requirements. You should carry out your own testing to determine the applicability of such information and whether the product will be suitable. CHT reserve the right to modify the technical data sheet at any time. The CHT technical service department is available to offer further information and advice and should it be needed to look at modifying current products or custom formulate a new one to meet your specific requirements. Please contact the technical service department.

CHT Germany GmbH: Postfach 12 80, 72002 Tübingen, Bismarckstraße 102, 72072 Tübingen, Germany
Telephone: 07071/154-0, Fax: 07071/154-290, Email: info@cht.com, Homepage: www.cht.com / www.cht-silicones.com

| | |
|---------------|-------------|
| Revision Date | 28 Jun 2022 |
| Revision No | 4 |
| Download Date | 30 Apr 2024 |