

AS5600 Trans 1 Part General Purpose Sealant

Description

This is a 1-part, RTV (Room Temperature Vulcanising) silicone adhesive sealant. It is one in a range of Oxime cure products which are solvent free. It exhibits good primerless adhesion to many substrates especially plastics and cures rapidly at room temperature when in contact with atmospheric moisture. This product can be described as low corrosive but would not be recommended for use with copper or its associated alloys.

Key Features

- Good adhesion to many substrates
- Complies with BS5889 type A
- US Federal TT-S-001543A class A
- Germany DIN 18540

Application

Applications include but are not limited to, aquarium tunnels, glazing, sealing of lead flashing and sealing of masonry.

Use and Cure Information

This product is a ready for use 1 Part system. If supplied in cartridges it can be applied using either manual or pneumatic dispensing guns. It can also be applied from bulk containers using conventional drum dispensing equipment.

All surfaces to which the sealant is to be applied should be clean, dry and free from grease, dirt, and loose material. Priming of surfaces is not normally required. If using as an adhesive, it should be applied to one clean surface and the other clean surface brought into contact with it within the tack free time stated opposite. For optimum bond strength, the thickness of the sealant joint should be a minimum of 1 mm.

The sealant will cure upon exposure to atmospheric moisture, ideally between 20 to 30 °C and 40% to 70% Relative Humidity. Time taken for cure will depend on the thickness of the joint, humidity and temperature. Joints should be left undisturbed for at least 24 hours, but preferably longer to effect sufficient depth of cure. Full cure requires 7 days.

"For pneumatic dispensing of 310 ml cartridges, the recommended pressure is 2.25 to 3.45 bar (40 to 50 psi). Dispensing pressure above the recommended limits may lead to gas bypassing the piston, causing spluttering at the nozzle and poor bead quality"

Health & Safety

Health and Safety

Safety Data Sheets available on request.

Packaging

CHT Adhesives are available in a variety packaging including cartridges and bulk containers. Please contact our sales department for more information.

Revision Date 29 Apr 2021
Revision No 1
Download Date 14 May 2024

Property

Uncured Product

Property	Test Method	Value
Appearance		Thixotropic paste
Cure Profile		23+/-2°C and 50+/-5% humidity
Cure Through to 3 mm Depth		12 hr
Cure Type		Oxime
Rheology		Paste
Self Bonding		Yes
Slump		1 mm/5mins
Tack Free Time / Skin Formation at 23°C/73°F		7 min

Cured Product

Property	Test Method	Value
7 days at 23+/-2°C and 60+/-5% humidity		
100% Modulus (N/mm2)		0.33 MPa / 48 psi
Color		Translucent
Elongation at Break	ISO 37	530 %
Hardness Shore A	ASTM D 2240-95	28
Max Working Temp		180 °C / 356 °F
Min Working Temp		-50 °C / -58 °F
Tensile Strength	ISO 37	1.12 N/mm2 / 162 psi
Youngs Modulus (N/mm2)		0.18 N/mm2 / 26 psi

Adhesion Testing

Lap Shear Aluminium kg/cm ²	ASTM D1002	5.85 kg/cm ²
Lap Shear Stainless Steel 304 kg/cm ²	ASTM D1002	8.35 kg/cm ²

Storage

Max Storage Temperature	40 °C / 104 °F
Shelf Life	18 mths