

CHT-BeauSil™ PEG 205 Modified polysiloxane as an ingredient for Personal Care.

Description

Organo modified Silicone polymer for the use as ingredient in Personal Care applications. The unique product allows to formulate high end formulations.

Key Features

- Cleansing effect
- Emulsifier, Dispersing and Solubilizing properties
- Enhances Spreading and Foam stabilizing
- Emollient and Conditioning agent


Key Applications

- Hair Care
- Skin Care
- Color Cosmetic


Application

CHT-BeauSil™ PEG 205 is a polyether-functionalised siloxane used in various personal care applications. It is compatible with a wide range of cosmetic ingredients and provides stable formulations. CHT-BeauSil™ PEG 205 can be used as lubricant in shampoos or shower gels. In hair care formulation such as hair sprays CHT-BeauSil™ PEG 205 is used as plasticising agent for polymers. CHT-BeauSil™ PEG 205 can be used in shaving foams as foam stabiliser and for improving the gliding properties.

Structure examples of Silicone Emulsifiers / Surfactants



Example for PEG/PPG Dimethicone



Example for Alkyl-PEG/PPG Dimethicone

Use and Cure Information

Stir before use.

Health & Safety

Safety Data Sheets available on request.

Packaging

Drums and bulk containers. Please contact our sales department for more information

Revision Date 08 Dec 2021
Revision No 3
Download Date 14 May 2024

Property

Product

Appearance
INCI Name
Ionicity
MIT Free
Non-Volatile Content (%)
Ultralow cyclic content
Viscosity

Test Method

Value

Colourless to yellow liquid
PEG-12 dimethicone
Non-ionic
Yes
Approx. 100
Yes
Brookfield <800 cP

Addition Rates

Dosage - 1
Dosage - 2
Dosage - 3

0.1 – 2.0% in cleansing formulations
0.5 - 3.0% as emulsifier
0.3 - 3.0% as emollient / conditioning agent

Solubility

Solubility - Almond oil
Solubility - Cetyl Dimethicone
Solubility - Dimethicone 350cst
Solubility - Ethanol
Solubility - Ethylhexylcarbonate
Solubility - Glycerine
Solubility - IPM
Solubility - Isododecane
Solubility - Paraffin Oil
Solubility - Polysorbate-20
Solubility - Propylenglycol
Solubility - Water

Miscible
Miscible
Miscible
Soluble
Insoluble
Miscible
Insoluble
Soluble
Miscible
Soluble
Miscible
Soluble

Storage

Max Storage Temperature
Min Storage Temperature
Shelf Life

40 °C / 104 °F
4 °C / 39 °F
24 mths

The content set out in the technical data sheet does not contain information upon which you should rely. It is provided for general information purposes only and does not constitute a product specification. You must obtain professional or specialist advice before taking any action based on the information provided in the technical data sheet. CHT make reasonable efforts to ensure that information set out in the technical data sheet is complete, accurate, and up-to-date. CHT do not, however, make any representations, warranties or guarantees (whether express or implied) that information set out in the technical data sheet is complete, accurate, or up-to-date or that the product will be suitable for your requirements. You should carry out your own testing to determine the applicability of such information and whether the product will be suitable. CHT reserve the right to modify the technical data sheet at any time. The CHT technical service department is available to offer further information and advice and should it be needed to look at modifying current products or custom formulate a new one to meet your specific requirements. Please contact the technical service department.

CHT Germany GmbH: Postfach 12 80, 72002 Tübingen, Bismarckstraße 102, 72072 Tübingen, Germany
Telephone: 07071/154-0, Fax: 07071/154-290, Email: info@cht.com, Homepage: www.cht.com / www.cht-silicones.com