

EM 1670 RTU 10% Polydimethylsiloxane emulsion

Description

This product is an industrial nonionic polydimethylsiloxane emulsion.

Key Features

- Ready-to-use silicone and preservative levels
- Thick, creamy, clinging viscosity to promote application on vertical surfaces
- Compatible with cationic, anionic, and nonionic systems
- Uniform deposition on surfaces

Key Applications

- Auto care
- Polish formulations
- Leather conditioning
- Multipurpose release agent

Application

EM 1670 RTU is a 10% active emulsion of 350 cSt polydimethylsiloxane. Because of its non-ionic nature, it can be used in a variety of systems, such as non-ionic, anionic, cationic surfactant or polymer systems without forming a complex. EM 1670 RTU delivers 350 cSt PDMS in an industry-leading fine particle size emulsion, permitting a wider range of applications and storage conditions than the competition. EM 1670 RTU's increased viscosity permits easy application on vehicle surfaces.

Use and Cure Information

To optimize the dispersion of this emulsion into the final formulation, it is recommended to add it slowly at the end of the procedure at a temperature below 40 °C (104 °F) with continuous mixing or stirring.

Health & Safety

Read product and safety data sheets before handling this product for physical and health hazard information. The safety data sheet is available from your CHT representative.

Limitations

This product is not intended for pharmaceutical use.

Property	Test Method	Value
Product		
Appearance		Milk White
Ionicity		Non-ionic
Solids Content (%)		10 %
pH		8.0
Addition Rates		
Dosage - 1		Ready to use
Storage		
Max Storage Temperature		40 °C / 104 °F
Min Storage Temperature		4 °C / 39 °F
Packaging		40 lb. pails, 441 lb. drums, or 2205 lb. totes
Shelf Life		12 mths

Revision Date 22 Sep 2021

Revision No 7

Download Date 14 May 2024

The content set out in the technical data sheet does not contain information upon which you should rely. It is provided for general information purposes only and does not constitute a product specification. You must obtain professional or specialist advice before taking any action based on the information provided in the technical data sheet. CHT make reasonable efforts to ensure that information set out in the technical data sheet is complete, accurate, and up-to-date. CHT do not, however, make any representations, warranties or guarantees (whether express or implied) that information set out in the technical data sheet is complete, accurate, or up-to-date or that the product will be suitable for your requirements. You should carry out your own testing to determine the applicability of such information and whether the product will be suitable. CHT reserve the right to modify the technical data sheet at any time. The CHT technical service department is available to offer further information and advice and should it be needed to look at modifying current products or custom formulate a new one to meet your specific requirements. Please contact the technical service department.

CHT Germany GmbH: Postfach 12 80, 72002 Tübingen, Bismarckstraße 102, 72072 Tübingen, Germany
Telephone: 07071/154-0, Fax: 07071/154-290, Email: info@cht.com, Homepage: www.cht.com / www.cht-silicones.com