# TECHNICAL DATA SHEET



# **QGel 322** General purpose silicone gel

•
QGels are addition-cure clear, soft, moderately cross-linked
silicone polymer. Silicone gels provide protection from moisture,
vibration, thermal, or mechanical shock.

### **Key Features**

Description

- 1:1 mix ratio
- 24-hour room temperature cure
- Soft, but resilient gel
- Dispensing equipment not necessary

#### **Use and Cure Information**

#### **Important**

In order to achieve optimum performance, the same lot number of the A and B components should be used. Mixed lots may not obtain the performance criteria listed on the TDS or Certificate of

The "A" part of QGels contain the platinum catalyst; great care should be taken when using automated dispensing equipment to not cross-contaminate systems.

Both the "A" and "B" parts should be well stirred to ensure the material is uniform. QGels should be mixed by weight. Once the components are mixed, the curing process begins. The gel time of the mixed material is listed under the typical properties. Fast curing gels should be dispensed utilizing automated mix and dispensing equipment. In order to achieve optimum performance, the same "A" and "B" side lot numbers should be used.

## **De-Aeration**

Air trapped during mixing should be removed to eliminate voids in

the cured product. Vacuum de-airing may be necessary to completely remove all entrapped air bubbles. To ensure proper de-airing, subject the mixed material to 29 inches of mercury.

Weight) mm

Max Storage Temperature

Storage

Shelf Life

## Storage and Shelf-life

This product is best when used within 24 months from the date of manufacture, See product label and/or the CoA for specific "use by date". Product should be stored in its original, unopened container in an environment that does not exceed 38C (100F)

Storage beyond the date specified on the label does not necessarily mean that the product is no longer usable. In this case, the properties required for the intended use should be checked for quality assurance reasons.

**Revision Date** 16 Sep 2021

Revision No

Download Date 14 May 2024

Property	Test Method	Value
<b>Uncured Product</b>		
Cure Profile		20 mins at 150°C, 60 mins at 100°C, 24 hrs at 25°C
Cure Type		Addition
Density A	BS ISO 2781	0.97
Density B	BS ISO 2781	0.97
Gel Time at 25°C/77°F		30 min
Mix Ratio By Weight		1:1
Rheology		Gel
Viscosity A	Brookfield	750 cP
Viscosity B	Brookfield	750 cP
<b>Cured Product</b>		
Color		Transparent
Max Working Temp		204 °C / 399 °F
Min Working Temp		-55 °C / -67 °F
Penetration (19.5g Cone		4 - 8 mm

4 - 8 mm

24 mths

38 °C / 100 °F