

QSil Matting Agent Matte Surface Finish Additive

Description

This results in a matte finish on select silicone elastomer products when used at the appropriate levels. The matte finish will appear on the exposed surface of the silicone elastomer within 24 – 48 hours.

Key Features

- 100% Solids content
- Recommended level 0.5% - 1.0%

Key Applications

- Reduces the Coefficient of Friction (CoF)

Application

QSil Matting Agent is an additive to achieve a matte finish and can be used with most addition (platinum) or condensation (tin) cure silicone elastomers.

Use and Cure Information

MIXING

For best results, add to the base component at a 0.5 % – 1.0 % level and thoroughly mix. It is recommended that a small test batch be run to ensure that the appropriate level has been added. The matte finish will appear on the exposed surface of the silicone elastomer.

The matting agent can, in some cases, cause inhibition in addition cure systems. Additionally, the matting effect may not be as pronounced in a heat cure system and may, in fact, not appear at all depending on the composition of the elastomer. The matting agent can also cause a yellow finish to appear on the surface of the material it is being used with, particularly when used at higher levels. In addition, the yellowing may become darker as the material ages.

Property

Uncured Product

Color

Flash Point °C

Specific Gravity

Test Method

BS 2000-34

Value

Blue

>140 °C

0.935

Storage

Max Storage

Temperature

Shelf Life

38 °C / 100 °F

12 mths

Revision Date 12 Oct 2021
Revision No 4
Download Date 14 May 2024

The content set out in the technical data sheet does not contain information upon which you should rely. It is provided for general information purposes only and does not constitute a product specification. You must obtain professional or specialist advice before taking any action based on the information provided in the technical data sheet. CHT make reasonable efforts to ensure that information set out in the technical data sheet is complete, accurate, and up-to-date. CHT do not, however, make any representations, warranties or guarantees (whether express or implied) that information set out in the technical data sheet is complete, accurate, or up-to-date or that the product will be suitable for your requirements. You should carry out your own testing to determine the applicability of such information and whether the product will be suitable. CHT reserve the right to modify the technical data sheet at any time. The CHT technical service department is available to offer further information and advice and should it be needed to look at modifying current products or custom formulate a new one to meet your specific requirements. Please contact the technical service department.

CHT Germany GmbH: Postfach 12 80, 72002 Tübingen, Bismarckstraße 102, 72072 Tübingen, Germany
Telephone: 07071/154-0, Fax: 07071/154-290, Email: info@cht.com, Homepage: www.cht.com / www.cht-silicones.com